

CONCRESlVE® 1438

General purpose, epoxy bonding paste

DESCRIPTION

Concresive 1438 is a two part, epoxy resin based bonding paste for general purpose bonding.

The two parts are distinctly coloured to facilitate proper mixing - a white coloured Part 'A' and a black coloured Part 'B', which on correct mixing in the ratio 2:1 (A:B) by volume, yields a smooth bonding paste.

RECOMMENDED FOR

Concresive 1438 is recommended for use as an adhesive to bond most surfaces used in general construction ;

- pinning loose or broken tiles and masonry.
- bonding rubber, plastics, foam and other such flexible materials onto metal, concrete and other rigid materials.
- fairing uneven or very rough surfaces.
- filling gaps, joints and voids.

FEATURES AND BENEFITS

Non sag gel consistency Advantage in vertical or overhead applications.

Bonds to damp surfaces Avoids expensive surface preparation to achieve completely dry substrates.

Tough Tenacious adhesion. Withstands impact loads..

Different coloured components Visual indication of correct mixing. Avoidance of blending errors.

Convenient mix ratio Easy to proportion during application. Saves time.

TYPICAL PERFORMANCE DATA

(after 7 days cure)

Tensile strength @ 30°C	: 24 N/mm ²
Elongation at break (ASTM D638)	: 0.7%
Compressive modulus (ASTM D695)	: 2750 N/mm ²
Slant shear strength	: 34 N/mm ²
Compressive yield strength	: 69 N/mm ²

PROPERTIES

	Part A	Part B
Form	Paste	Viscous liquid
Colour	White	Black
Density (mixed)	: 1200 - 1250 kg/L	
Non-sag thickness @ 35°C (ASTM D2730)	: 13 mm	

Heat deflection temperature (ASTM D648) : 48°C

Application temperature, Min : 5°C
Max : 35°C

Curing properties

	@ 4°C	@ 21°C	@ 35°C
Pot life. (100 g)	120 mins	40 mins	25 mins
Min. open time	5 hrs	3 hrs	2 hrs
Initial cure (AASHTO T- 237)	7 days	1 day	1 day
Cure time (ASTM D695),	21 days	7 days	2 days

APPLICATION

Depending on the application, **Concresive 1438** can be used neat or filled with graded sand in the specified ratio.

- As a bonding paste : Use neat.
- As a fairing paste : Use neat.
- As a fairing mortar : Use sanded, in the ratio 1:1 (dry graded sand : **Concresive 1438**) by volume.

Surface preparation

Correct substrate preparation is critical for optimum performance. Surfaces should be structurally sound, clean, and free from loose particles, oil, grease, or any other contaminants.

Remove oil grease and wax contaminants by scrubbing with industrial grade detergent or degreasing compounds followed by mechanical cleaning.

Cement laitence, loose particles, mould release agent, curing membrane, and other contaminants must be removed from the surface by shotblasting (blastracking), scarifying or gritblasting followed by vacuum cleaning.

In case of steel surfaces remove grease and oil with suitable industrial grade cleaning and degreasing compounds. Remove rust and mill scale by gritblasting. Blast steel to white metal followed by vacuuming or blowing clean using oil-free, dry air.

If totally dry surface is impossible to achieve, blow clean any free water from the surface using oil-free air blast.

Concresive 1438 bonds to damp surfaces though a superior bond is achieved between completely dry surfaces.

Mixing

Mechanical mixing is necessary. A slow speed (600 rpm) drill with a grout stirrer is recommended.

Ideally, the entire contents of both Part A and Part B containers should be mixed together to avoid batching errors.

However, if part mixing is necessary, stir each component individually and then measure out precisely each component in the simple ratio of 2:1 (A:B) by volume into a clean, dry pail for subsequent mixing. Ensure that the leftover in each container is not contaminated.

Mix Part A and Part B together until the streaks of black and white disappear to yield a homogeneous grey mixture.

If needed, add dry, graded sand to the mixture and continue mixing for a further 2 minutes to get a lump free mix. Mix only quantities that can be consumed within the pot life of the product to avoid wastage.

Placing

Apply **Concresive 1438** within its pot life.

For bonding : Trowel apply **Concresive 1438** to a thickness of 0.8 to 3 mm depending on the job, so as to allow for a small quantity of the bonding paste to extrude out of the bond line when pressure is applied to the two surfaces.

For deep surface irregularities : Firmly trowel the sanded bonding paste to fill in the deep irregularities, and finish to a smooth surface.

CURING

Concresive 1438 is self curing. The curing time depends on the ambient temperature, the quantity mixed and placed. At 35°C, it will attain initial cure within 1 hr and full cure in 2 days.

CLEANING

Clean the tools and equipment first with rags, then wipe off using a solvent such as acetone, or methylene chloride before the bonding agent hardens.

ESTIMATING DATA

Actual consumption of **Concresive 1438** depends on the sand content, thickness of the coat, surface profile, loss and wastage. Typical coverage for the unsanded mix for a 3 mm thick coat ranges from 0.15 m²/L on rough surfaces to 0.33 m²/L on smooth surfaces.

Therefore, on smooth surfaces, for a 1 mm thick application, the consumption will be 1.0 L/m².

PACKAGING

Concresive 1438 is available in 1 L and 15 L sets. The components of **Concresive 1438** are available in the following packaging.

Component	Packaging	
	1 L set	15 L set
Part A	0.67 L	10.00 L
Part B	0.33 L	5.00 L

SHELF LIFE

Concresive 1438 can be stored in unopened original packing for 12 months, if stored at a temperature below 35°C.

PRECAUTIONS

Health : **Concresive 1438** contains certain chemicals which can cause skin irritation if exposed and respiratory reaction if inhaled. Wear gloves, mask and use barrier creams such as Kerodex No 71 while handling the product. Wash thoroughly after handling.

Should skin contact occur wash immediately with soap and water, or an effective hand cleaner.

In case of accidental eye contact wash with copious quantity of water and seek medical help immediately.

If ingested, do not induce vomiting. Consult doctor immediately.

The vapours of solvents used for cleaning can be irritating. It is therefore recommended that cleaning is done in a well ventilated area.

Fire : Product is combustible. Avoid exposure to naked flame. Do not smoke while handling the product.

SCr1438/2/0998

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **MBT** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **MBT** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **MBT**, are responsible for carrying out procedures appropriate to a specific application.

Construction Systems Asia Pacific Offices

REGIONAL HEADQUARTERS

MBT Asia Pacific
Tel : (65) 6861 6766
Fax: (65) 6863 0951

AUSTRALIA
MBT (Australia) Pty Ltd
Tel : (61) 2 9624 4200
Fax: (61) 2 9624 7681

CHINA
Shanghai Master Builders Co. Ltd
Tel : (86) 21 6485 3300
Fax: (86) 21 6495 1662

Guangzhou MBT Co., Ltd
Tel : (86) 20 8336 4978
Fax: (86) 20 8339 6468

Master Builders Technologies (Hong Kong) Ltd
Tel : (852) 2 407 4291
Fax: (852) 2 406 7391

INDONESIA
PT MBT Indonesia
Tel : (62) 21 893 4339
Fax: (62) 21 893 4342

JAPAN
Pozzolith Bussan Co., Ltd.
Tel : (81) 3 3582 0761
Fax: (81) 3 3583 3800

KOREA
Korea Master Builders Co. Ltd
Tel : (82) 2 3473 4891
Fax: (82) 2 3473 7869

MALAYSIA
MBT (Malaysia) Sdn Bhd
Tel : (60) 3 3344 3388
Fax: (60) 3 3344 2288

NEW ZEALAND
MBT (New Zealand) Ltd
Tel: (64) 9 414 7233
Fax:(64) 9 414 7244

PHILIPPINES
MBT (Philippines) Inc
Tel : (63) 2 838 4827-9
Fax: (63) 2 838 4830

SINGAPORE
MBT (Singapore) Pte Ltd
Tel : (65) 6861 6766
Fax: (65) 6861 3186

TAIWAN
MBT (Taiwan) Co. Ltd
Tel : (886) 2 2808 5055
Fax: (886) 2 2808 5066

THAILAND
Thai Master Builders Co. Ltd
Tel : (66) 2 681 1020
Fax: (66) 2 681 1034

VIETNAM
MBT (Vietnam) Ltd
Tel : (84) 650 743 100
Fax : (84) 650 743 200